### **EXPANSION PEX**

SUBMITTAL SHEET

## **Expansion PEX**

# **PEX-A Pipe**

PEX-A tubing is cross-linked, high-density polyethylene. All Apollo® Expansion PEX is opaque in color and is available with black, red, or blue print lines for easy identification of hot, cold, and main water lines. Apollo® uses the high-pressure peroxide method of cross-linking which is also known as PEX-A.

Apollo® Expansion PEX pipe is produced using the high-pressure peroxide method for crosslinked polyethylene (PEXa) in accordance with ASTM F876, F877, CSA B137.5 and PPI TR-3, and is certified to NSF 14/61 standards. Apollo® Expansion PEX pipe also meets the requirements of ASTM F2023 for chlorine resistance. Apollo® Expansion PEX pipe is manufactured using a quality management system which has been certified to the latest version of ISO 9001

Use of Apollo® Expansion PEX pipe in heating systems requires corrosion protection and/or isolation by using a heat exchanger or non-ferrous components throughout the system.

#### Features:

- Superior flexibility allows for fewer joints, thus reducing leak points
- Expandable and allows for "full flow"
- Less coil memory than traditional PEX pipe and resists the urge to remain coiled
- Compatible with both expansion and crimp, clamp or sleeve methods of joining
- Heat-repairable if kinked during installation, thus further eliminating additional repair connections
- Shape memory inherent in PEX-A tubing results in the shrinking of expanded pipe to normal size, creating strong, durable, and reliable ASTM F1960 fitting connections
- Maximum cross-linking increases flexibility and resistance to cracking
- Copper tube size dimensions (CTS)
- · Available in black, red, or blue print lines
- Approved for use with brass and poly alloy crimp fittings (ASTM F1960 and ASTM 1807)
- 25 year warranty

#### Standards / Certifications:

PEX 3006 - SDR 9
Meets or exceeds: ASTM F876/F877/F1807/F1960/F2023/F2080/F2155

• cNSFus-pw • Meets ANSI/NSF 61 & 14 • cUPC • Meets CSA B137.9

#### **Maximum Pressures & Temperatures:**

• 160 psi @ 73.4° F (1055 kPa @ 23° C), 100 psi @ 180° F (690 kPa @82.2° C), 80 psi @ 200° F (550 kPa @ 93.3° C) Design factor 0.50 (per ASTM F876, CSA B137.5)

#### Installation:

Cut PEX tubing at a 90° angle using a PEX tubing cutter. Clear the cut end of any burrs or debris. PEX tubing can be run through holes drilled into the center of studs or by using straps and hangers. Bend supports can be used to make bends and angles instead of having to cut the tubing and use fittings. A variety of barb insert fittings or push type fittings can be used with PEX tubing. **DO NOT expose PEX tubing to direct sunlight.** It is recommended to insulate hot water lines with standard foam polyethylene pipe insulation to prevent heat loss. If installing in an area that experiences harsh winters, it's recommended to insulate both hot and cold water lines to prevent freezing.

 $Compatible \ with \ Uponor \ (Wirsbo) \ ProPEX^{\tiny{TM}}. \ (\textit{ProPEX}^{\tiny{TM}} \textit{is a trademark of Uponor [Wirsbo].})$ 












Article No.	Nom. Size in	Avg OD A in (mm)	Min. Wall Thickness B in (mm)	Weight lb/ft (kg/m)	Capacity gal/ft (I/m)
EPPBXXX12 EPPRXXX12 EPPWXXX12	1/2	0.625 (15.88)	0.070 (1.78)	0.06 (0.08)	0.0098 (0.1222)
EPPBXXX34 EPPRXXX34 EPPWXXX34	3/4	0.875 (22.22)	0.097 (2.47)	0.10 (0.15)	0.0189 (0.2356)
EPPBXXX1 EPPRXXX1 EPPWXXX1	1	1.125 (28.58)	0.125 (3.18)	0.17 (0.26)	0.0316 (0.3939)

Specification	English	SI	Standard	
Min. Density	Min. Density 58 lb/ft		ASTM F876	
Min. Degree of Crosslinking	70%	70%	ASTM F876	
Max. Thermal Conductivity	2.84 Btu in/(ft°F hr)	0.41 W/(m°K)	DIN 16892	
Coefficient of Linear Expansion	9.33 x 10-4 in/ ft°F @ 68°F 1.33 x 10-3 in/ ft°F @ 212°F	0.14 mm/(m°C) @ 20°C 0.2 mm/(m°C) @ 100°C	Mean @ 20-70°C per DIN 16892	
Modulus of Elasticity	87,000-130,500 psi @ 68°F 43,500-58,000 psi @ 176°F	600-900 N/mm @ 20°C 300-400 N/mm @ 80°C	Minimum @ 20°C per DIN 16892	
Tensile Strength	4194-4355 psi @ 68°F 2610-2900 psi @ 176°F per ASTM D638	26-30 N/mm @ 20°C 18-20 N/mm @ 80°C per ASTM D638	-	
IZOD Impact Resistance	No Break	No Break	-	
Roughness	e=0.00028 in	e=0.007 mm	-	
Temperature Working Range	-40 to 200°F	-40 to 93°C	-	
Max. Short-term Exposure	150 psig @ 210°F (48 hr)	1035 kPa @ 99°C (48 hr)	ASTM F876	
UV Resistance	_	_	ASTM F2657	




The maximum temperature and pressure ratings of Apollo® Expansion PEX pipe are in accordance to ASTM F876, CSA B137.5 and PPI TR-3. The designer shall determine the actual conditions and apply the appropriate and additional design factors as required for any particular project. The temperature and pressure ratings apply to the application of Apollo® Expansion PEX pipe for conveying heating and cooling water at the 2.0 safety factor on allowable working pressure according to ASTM and CSA. According to the Apollo® Expansion PEX warranty, the warranty period of 25 years is for operating conditions at or below 180°F (82.2°C) in permitted applications when the handling, use, installation and maintenance continually complies with all Apollo® Expansion PEX technical guidelines.

## **EXPANSION PEX**




	Blue Print Line PEX Tubing					
	Part #	Size (CTS)	Length	O.D.	Nom. I.D.	
	EPPB10012	1/2"	100'	0.625±.004	0.475	
Ī	EPPB30012	1/2"	300'	0.625±.004	0.475	
	EPPB10034	3/4"	100'	0.875±.004	0.671	
	EPPB30034	3/4"	300'	0.875±.004	0.671	
	EPPB1001	1"	100'	1.125±.005	0.862	
ľ	EPPB3001	1"	300'	1.125±.005	0.862	





Red Print Line PEX Tubing					
Part #	Size (CTS)	Length	O.D.	Nom. I.D.	
EPPR10012	1/2"	100'	0.625±.004	0.475	
EPPR30012	1/2"	300'	0.625±.004	0.475	
EPPR10034	3/4"	100'	0.875±.004	0.671	
EPPR30034	3/4"	300'	0.875±.004	0.671	
EPPR1001	1"	100'	1.125±.005	0.862	
EPPR3001	1"	300'	1.125±.005	0.862	





White PEX Tubing					
Part #	Size (CTS)	Length	O.D.	Nom. I.D.	
EPPW512	1/2"	5'	0.625±.004	0.475	
EPPW1012	1/2"	10'	0.625±.004	0.475	
EPPW2012	1/2"	20'	0.625±.004	0.475	
EPPW10012	1/2"	100'	0.625±.004	0.475	
EPPW30012	1/2"	300'	0.625±.004	0.475	
EPPW50012	1/2"	500'	0.625±.004	0.475	
EPPW100012	1/2"	1,000'	0.625±.004	0.475	
EPPW534	3/4"	5'	0.875±.004	0.671	
EPPW1034	3/4"	10'	0.875±.004	0.671	
EPPW2034	3/4"	20'	0.875±.004	0.671	
EPPW10034	3/4"	100'	0.875±.004	0.671	
EPPW30034	3/4"	300'	0.875±.004	0.671	

